


The following listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

- Sub 1 1. (Amended): An electro-optical liquid-crystal display comprising a realignment layer, for realigning liquid crystals, and a liquid-crystalline medium of positive dielectric anisotropy,

wherein said medium comprises one or more compounds of formula I




wherein

B2 R¹ is alkenyl having 2 to 7 carbon atoms, alkenyloxy having 2 to 7 carbon atoms or alkoxyalkyl having 2 to 7 carbon atoms, and Y¹¹, and Y¹² and Y¹³ are each, independently of one another, H or F, and Y¹³ is H; and

wherein when an electric voltage is applied to said display an electric field is generated which has a component parallel to the liquid-crystal layer for realignment of the liquid crystals.


2. (Original): A liquid-crystal display according to Claim 1, wherein said medium comprises one or more compounds of formula II:




II

wherein



R^2 is alkyl having 1 to 7 carbon atoms, alkoxy having 1 to 7 carbon atoms, alkenyl having 2 to 7 carbon atoms, alkenyloxy having 2 to 7 carbon atoms or alkoxyalkyl having 2 to 7 carbon atoms,




are each, independently of one another,



and

at least one of  and  is




B2
cont.

X^2 is F, Cl or CN; and


Z^2 is $-\text{CH}_2\text{CH}_2-$, $-\text{COO}-$, $-\text{CF}_2\text{O}-$ or a single bond.

3. (Original): A liquid-crystal display according Claim 1, wherein said medium comprises at least one compound of formula III




wherein

R^{31} and R^{32} are each, independently of one another, alkyl having 1 to 7 carbon atoms, alkoxy having 1 to 7 carbon atoms, alkenyl having 2 to 7 carbon atoms, alkenyloxy having 2 to 7 carbon atoms or alkoxyalkyl having 2 to 7 carbon atoms,



Z^{31} is $-\text{CH}=\text{CH}-$, $-\text{COO}-$, $-\text{CH}_2\text{CH}_2-$ or a single bond.

4. (Original): A liquid-crystal display according Claim 2, wherein said medium comprises at least one compound of formula III




wherein

R^{31} and R^{32} are each, independently of one another, alkyl having 1 to 7 carbon


B2
cont.

atoms, alkoxy having 1 to 7 carbon atoms, alkenyl having 2 to 7 carbon atoms, alkenyloxy having 2 to 7 carbon atoms or alkoxyalkyl having 2 to 7 carbon atoms,




Z^{31} is $-\text{CH}=\text{CH}-$, $-\text{COO}-$, $-\text{CH}_2\text{CH}_2-$ or a single bond.

5. (Original): A liquid-crystal display according to Claim 1, wherein said medium comprises at least one compound of formula IV




wherein

R^4 is alkyl having 1 to 7 carbon atoms, alkoxy having 1 to 7 carbon atoms, alkenyl having 2 to 7 carbon atoms, alkenyloxy having 2 to 7 carbon atoms or alkoxyalkyl having 2 to 7 carbon atoms,



are each, independently of one another,




Z^{41} and Z^{42} are each, independently of one another, $-\text{CF}_2\text{O}-$, $-\text{COO}-$, $-\text{CH}_2\text{CH}_2-$ or a single bond,

n is 0 or 1,

X is OCF_3 , OCF_2H or F , and


Y^{41} and Y^{42} are each, independently of one another, H or F .

6. (Original): A liquid-crystal display according to Claim 2, wherein said medium comprises at least one compound of formula IV




wherein

R^4 is alkyl having 1 to 7 carbon atoms, alkoxy having 1 to 7 carbon atoms, alkenyl having 2 to 7 carbon atoms, alkenyloxy having 2 to 7 carbon atoms or alkoxyalkyl having 2 to 7 carbon atoms,



are each, independently of one another,




Z^{41} and Z^{42} are each, independently of one another, $-\text{CF}_2\text{O}-$, $-\text{COO}-$, $-\text{CH}_2\text{CH}_2-$ or a single bond,

n is 0 or 1,

X is OCF_3 , OCF_2H or F , and

Y^{41} and Y^{42} are each, independently of one another, H or F .


7. (Original): A liquid-crystal display according Claim 3, wherein said medium comprises at least one compound of formula IV




IV

wherein

R^4 is alkyl having 1 to 7 carbon atoms, alkoxy having 1 to 7 carbon atoms, alkenyl having 2 to 7 carbon atoms, alkenyloxy having 2 to 7 carbon atoms or alkoxyalkyl having 2 to 7 carbon atoms,



are each, independently of one another,




Z^{41} and Z^{42} are each, independently of one another, $-\text{CF}_2\text{O}-$, $-\text{COO}-$, $-\text{CH}_2\text{CH}_2-$ or a single bond,

n is 0 or 1,

X is OCF_3 , OCF_2H or F , and


Y^{41} and Y^{42} are each, independently of one another, H or F .

8. (Original): A liquid-crystal display according to Claim 4, wherein said medium comprises at least one compound of formula IV




wherein

R^4 is alkyl having 1 to 7 carbon atoms, alkoxy having 1 to 7 carbon atoms, alkenyl having 2 to 7 carbon atoms, alkenyloxy having 2 to 7 carbon atoms or alkoxyalkyl having 2 to 7 carbon atoms,



are each, independently of one another,




Z^{41} and Z^{42} are each, independently of one another, $-\text{CF}_2\text{O}-$, $-\text{COO}-$, $-\text{CH}_2\text{CH}_2-$ or a single bond,

n is 0 or 1,


X is OCF_3 , OCF_2H or F , and

Y^{41} and Y^{42} are each, independently of one another, H or F .


9. (Original): A liquid-crystal display according to Claim 2, wherein medium comprises one or more compounds of formulae IIa to IIg




IIa




IIb




IIc




IId



IIe



IIf




IIg

B2
cont.


10. (Original): A liquid-crystal display according to Claim 4, wherein medium

comprises one or more compounds of formulae IIa to IIg




IIa


B₂
cont.




IIb




IIc




IId



IIe





IIf



IIg

B2
cont.

11. (Original): A liquid-crystal display according Claim 3, wherein said medium comprises one or more compounds of formulae IIIa to IIIc



wherein

k is 1, 2, 3, 4 or 5,

m and n are each 0, 1, 2 or 3,

m + n is ≤ 5 , and

o is 0 or 1.

12. (Original): A liquid-crystal display according to Claim 8, wherein said medium comprises


- 1 to 35% of one or more compounds of the formula I,
- 3 to 30% of one or more compounds of the formula II,
- 3 to 45% of one or more compounds of the formula III,
- and
- 5 to 60% by weight of at least one compound of the formula IV.

13. (Original): A liquid-crystal display according to Claim 1, wherein pixels of the display are addressed by means of an active matrix.

14. (Amended): A liquid-crystalline medium of positive dielectric anisotropy comprising at least two liquid-crystal compounds

wherein at least one of said compounds is of formula I

B2
cont.




wherein


R^1 is alkenyl having 2 to 7 carbon atoms, alkenyloxy having 2 to 7 carbon atoms or alkoxyalkyl having 2 to 7 carbon atoms, ~~and~~
 Y^{11} , ~~and~~ Y^{12} ~~and~~ Y^{13} are each, ~~independently of one another, H or F, and~~
 Y^{13} is H. --

15. (Original): In a method of generating an electro-optical effect using a liquid-crystal display, the improvement wherein a display according to claim 1 is used to generate said effect.

16. (Original): A liquid-crystal display according to claim 1, wherein said medium additionally comprises one or more compounds of formulae Va and Vb




Va




Vb

in which R^{51} and R^{52} are each, independently of one another, alkyl or alkoxy having 1 to 7 carbon atoms or alkenyl, alkenyloxy or alkoxyalkyl having 2 to 7 carbon atoms, and/or
 one or more compounds of formulae Vc and Vd

B2
cont.



Vc



Vd

in which

R^{51} and R^{52} independently of one another, are as defined above, and Y^{51} is H or F.

17. (Original): A liquid-crystal display according to Claim 8, wherein said medium comprises

- 2 to 30% of one or more compounds of the formula I,
- 5 to 25% of one or more compounds of the formula II,
- 5 to 40% of one or more compounds of the formula III,
- and
- 5 to 50% by weight of at least one compound of the formula IV.

18. (Original): A liquid crystal display according to claim 1, wherein said medium has a birefringence of <0.12 , a flow viscosity at 20° of $<30 \text{ mm}^2 \bullet \text{s}^{-1}$, a resistivity at 20°C of 5×10^{10} to $5 \times 10^{13} \Omega \bullet \text{cm}$, a rotational viscosity at 20°C of $<130 \text{ mPa} \bullet \text{s}$, and a clearing point above 60°C .

19. (Original): A liquid-crystal display according to claim 1, wherein said medium has a birefringence of $0.05-0.11$.

20. (Original): A liquid-crystal display according to claim 1, wherein said medium has a flow viscosity at 20°C of $15-25 \text{ mm}^2 \bullet \text{s}^{-1}$.

21. (Original): A liquid-crystal display according to claim 1, wherein said medium has a resistivity at 20°C of 5×10^{11} to $5 \times 10^{12} \Omega \bullet \text{cm}$.

B2
cont.

22. (Original): A liquid-crystal display according to claim 1, wherein said medium has a rotational viscosity at 20°C of 70-110 mPa • s.

23. (Original): A liquid-crystal display according to claim 1, wherein said medium exhibits a storage stability of at least 1000 hours at -30°C.

B2
CONT. 24. (Previously Added): A display according to claim 1, wherein in formula I R¹ is 1E-alkenyl, 1E-alkenyloxy, or straight-chain alkoxyalkyl.

25. (Previously Added): A display according to claim 24, wherein in formula I R¹ has 2 to 5 carbon atoms.

26. (New): A liquid-crystal medium according to claim 14, wherein in formula I R¹ is 1E-alkenyl, 1E-alkenyloxy, or straight-chain alkoxyalkyl.

27. (New): A liquid-crystal medium according to claim 26, wherein in formula I R¹ has 2 to 5 carbon atoms.

28. (New): A display according to claim 1, wherein the concentration in said medium of each compound of formula I is 0.1 to 20%.

B3 29. (New): A display according to claim 28, wherein the concentration in said medium of each compound of formula I is 1 to 16%.

30. (New): A display according to claim 29, wherein the concentration in said medium of each compound of formula I is 3 to 10%.

31. (New): A medium according to claim 14, wherein the concentration in said medium of each compound of formula I is 0.1 to 20%.

32. (New): A medium according to claim 31, wherein the concentration in said

medium of each compound of formula I is 1 to 16%.


33. (New): A medium according to claim 31, wherein the concentration in said medium of each compound of formula I is 3 to 10%.

34. (New): A display according to claim 8, wherein said medium contains 2 to 30 % by weight of at least one compound of formula I, 5 to 25 % by weight of at least one compound of formula II, 5 to 40 % by weight of at least one compound of formula III, and 5 to 50 % by weight of at least one compound of the formula IV.

35. (New): A display according to claim 8, wherein said medium contains 3 to 20 % by weight of at least one compound of formula I, 5 to 18 % by weight of at least one compound of formula II, 10 to 30 % by weight of at least one compound of formula III, and 20 to 40 % by weight of at least one compound of the formula IV.

36. (New): An electro-optical liquid-crystal display comprising a realignment layer, for realigning liquid crystals, and a liquid-crystalline medium of positive dielectric anisotropy,

wherein said medium comprises one or more compounds of formula I




wherein

R¹ is alkenyl having 2 to 7 carbon atoms or alkenyloxy having 2 to 7 carbon atoms, and
Y¹¹, Y¹² and Y¹³ are each, independently of one another, H or F; and

wherein when an electric voltage is applied to said display an electric field is generated which has a component parallel to the liquid-crystal layer for realignment of the liquid crystals.

37. (New): A liquid-crystalline medium of positive dielectric anisotropy comprising at least two liquid-crystal compounds

wherein at least one of said compounds is of formula I



wherein

R¹ is alkenyl having 2 to 7 carbon atoms or alkenyloxy having 2 to 7 carbon atoms, and

Y¹¹, Y¹² and Y¹³ are each, independently of one another, H or F.

B3
cont.